



# SR2000

## Southeast Resins

## Tables

### SR2K Slurry Mix Tables Using MEKP Activator Pot Holes/Spalls

Volume SR2K	Activator Average Weather 70-85 F	Activator Hot Weather 85-105 F	Activator Cool Weather 50-70 F	Aggregate 3:1 Ratio	Yield Cubic Ft (Pot hole/Spall Filling)
1 QT	12 cc	10 cc	18 cc	3 QT	1/8 Cubic Foot
1/2 Gallon	25 cc	20 cc	35 cc	1.5 Gallon	1/4 Cubic Foot
1 Gallon	50 cc	40 cc	70 cc	3 Gallons	1/2 Cubic Foot
2 Gallon	100 cc	80 cc	140 cc	6 Gallons	1 Cubic Foot
3 Gallon	150 cc	120 cc	210 cc	9 Gallons	1 1/2 Cubic Foot
4 Gallon	200 cc	160 cc	280 cc	12 Gallons	2 Cubic Foot
5 Gallon	250 cc	200 cc	350 cc	15 Gallons	2 1/2 Cubic Foot

The above mix profiles are to be used only as a guideline. Please contact our 24 hour technical support to discuss specifics prior to job.